

BNX[®] 1225 TPR Antioxidant & SIS Thermoplastic Pelletized Blend

Introduction: BNX[®] 1225 TPR is a pelletized blend of BNX[®] 1225 and a SIS (styrene-isoprene-styrene) thermoplastic rubber. BNX[®] 1225 is a synergistic blend of BNX[®] 1010 and Benefos[®] 1680. This blend of both a primary and secondary antioxidant provides excellent heat stability and antioxidation, with good compatibility with resins and excellent extraction resistance. The SIS (styrene-isoprene-styrene) thermoplastic rubber has a styrene content of 14%, diblock content of 12% and a melt index of 9.


Material Description: Antioxidant and SIS Thermoplastic Rubber Pelletized Blend

Chemical Name: BNX[®] 1010: Tetrakis [Methylene-3 (3',5'-di-tert-butyl-4-hydroxyphenyl) propionate] methane
Benefos[®] 1680 : Tris (2, 4- di-tert-butylphenyl) phosphite
SIS: Styrene-isoprene-styrene Thermoplastic Rubber


Empirical Formula: C₇₃H₁₀₀O₁₂ (BNX[®] 1010)
C₄₂H₆₃O₃P (Benefos[®] 1680)
SIS: Proprietary

CAS #: 6683-19-8 (BNX[®] 1010)
31570-04-4 (Benefos[®] 1680)
25038-32-8 (SIS)

Chemical Structure:



SIS Rubber



Physical Properties:

Appearance: white opaque pellet
Pellet Weight: 0.6-1.2 g/50 pellet
BNX[®] 1225 concentration: 43-47%

Applications:

BNX[®] 1225 TPR is a 45:55 blend of BNX[®] 1225 and a SIS thermoplastic rubber in a pelletized form. This product is used in the manufacture of hot-melt pressure sensitive adhesives (HMPSA) using single or twin-screw extruders. This unique product can also be used with sigma mixers to achieve a more uniform dispersion of the antioxidant in the HMPSA. BNX[®] 1225 TPR is compatible with other SIS thermoplastic elastomers such as Quintac[®] 3620, Kraton D1161P, Kraton D1193, Enichem ST-190, and Vector 4113.

Advantages:

- Accurate Dispensing in Loss-In-Weight Feeders (i.e. K-Tron)
 - Uniform shape and size
 - Pellets are durable enough for air conveying (will not break-up)
 - High melt resistance / non-bridging or blocking
- Increased Processing efficiencies
 - Reduced handling time
 - Increased product dispersibility in twin screw extruders and sigma mixers
 - Compatible with standard antioxidant metering equipment
 - Minimal screw slippage
 - Dry and dust free
- Reduced Health Hazards
 - Caused by dust inhalation
 - Caused by prolonged skin contact
- Reduced fire and explosion hazards
 - Caused by electrostatic charge build-up – no powders

Loading Instructions:

The loading data and results are based on laboratory work (and field testing) under controlled conditions and do not necessarily indicate the result that the buyer or user will attain. For this reason we strongly recommend testing of your own system under the actual conditions of processing and end-use prior to full scale testing. Concentration levels of the antioxidant (BNX[®] 1225) in hot melt adhesives range from 0.2% to 1%. Therefore the feed rate of BNX[®] 1225 TPR should be 0.4% to 2%. Exact loading must be determined by compositions of the specific polymer system.

Packaging:

BNX[®] 1225 TPR is available in 50 lb PE bags in 800-lb (16 bags) Gaylord containers.

Storage:

This product may be stored up to two years in a closed container. Containers should be stored in a cool, dry area. Storage at elevated temperatures or exposure to direct heat or sunlight could reduce the product life and could result in clumping or blockage. Keep containers closed and in a cool dry area when not in use.

Toxicity & Safety:

This material is not intended for use in products for which prolonged contact with mucous membranes or abraded skin, or implantation within the human body is specially intended, unless the finished product has been tested in accordance with the Food and Drug Administration and/or other applicable safety testing requirements. Because of wide range of such potential uses, Mayzo, Inc. is not able to recommend this material as safe and effective for such uses and assumes no liability for any such uses. Read and understand the Material Safety Data Sheet before using or handling this product.

FDA Regulations:

The regulation status for BNX[®] 1225 TPR is derived from the single components. All three ingredients, BNX[®] 1010, Benefos[®] 1680, and SIS rubber, are approved in food contact application; however, please consult the individual data sheets for specific detailed information.

[Quintac[®] is a registered trademark of Zeon Chemicals.]

Revision: 11/30/06...ratio modification.

The information contained herein is believed to be reliable. However, Mayzo, Inc. makes no warranty, whether expressed or implied, including warranties of merchantability or of fitness for a particular purpose, for the product or products referred to herein. No statements or recommendations contained herein are to be constructed as inducements to infringe any relevant patent, now or hereafter existence. Under no circumstances shall Mayzo, Inc. be liable for incidental, consequential, or other damages from alleged negligence, breach of warranty, strict liability, or any other legal theory, arising out of the use of handling of the product or products referred to herein. The sole remedy of the buyer and sole liability of Mayzo, Inc. for any claims shall be limited to the buyers purchase price of the product which is subject of the claim or the amount actually paid for each product, whichever is less. Technical advice furnished by seller shall not constitute a warranty, which is expressly disclaimed, all such advice being given and accepted at the buyers risk.