

MAYZO

RA-110W
Water-based Release Coat



Norcross, Georgia
Corporate Headquarters

6577 Peachtree Industrial Boulevard • Norcross, Georgia 30092

Phone: (770) 449-9066 • Fax: (770) 449-9070

www.mayzo.com

RA-110W Release Coat

Introduction: RA-110W Release Coat is a non-silicone, fluoropolymer (acrylic backbone) water based emulsion which provides superior release characteristics when applied to many film types including polypropylene, polyethylene, and polyester. Metallized foil and paper substrates can also be coated.

Material Description: Fluoro-Acrylate Release Coat

Chemical Name: Fluoro-Acrylate

Empirical Formula: Proprietary Blend

CAS #: Mixture

Molecular Weight: Proprietary

Physical Properties:

Appearance:	Off white, milky emulsion
Ionic Characteristic:	Nonionic
Solids Content:	30%
Solvent:	60% Water 10% Dipropylene glycol
pH:	4.4 +/- 1
Specific Gravity:	1.1
Flash point:	>94 °C (>200 °F) [Closed cup]

Mixing Instructions: Depending on the type of substrate and pressure sensitive adhesive, the concentration of solid matter required should be determined by laboratory trial. RA-110W Release Coat diluted to between 0.5% to 3.0% solids will be adequate in most pressure sensitive applications. Stir well before use.

Applications: RA-110W Release Coat is diluted in water to achieve application concentrations. Depending on the substrate and adhesive, the solids concentration should be determined by lab test. Recommended levels are between 0.5 - 3.0%. Film substrates should be corona treated to ensure adhesion to the substrate. Coat at 4 - 5 gm/m² (wet coat weight) using conventional coating methods with Meyer rod, Anilox or Gravure rollers. Coated substrate must be thoroughly dry before rewinding.

Advantages:

- Offers a low noise release. The smooth release properties are superior to PVODC release coatings.
- Cost Efficient. Requires a smaller amount of material than silicone release coatings. Excellent release can be obtained using as little as 0.5% solids concentration, depending on film, adhesive, coating equipment and desired release levels. Only a near monomolecular film is required to achieve excellent results.
- Release effects are unaffected at temperatures up to 350° F.

- Unlike silicone, no diffusion into the adhesive means no contamination of the finished product.

Packaging: RA-110W Release Coat is available in 40 lb. (18.15 kg) pails (with an upcharge) and 441 lb. (200 kg) steel drums.

Storage: This product may have a flash back of flammable vapor. Store in sealed containers in approved storage areas. Avoid open flame, sparks, and high heat during use. Do not breathe vapors.

Toxicity & Safety: This material is not intended for use in products for which prolonged contact with mucous membranes or abraded skin, or implantation within the human body is specially intended, unless the finished product has been tested in accordance with the Food and Drug Administration and/or other applicable safety testing requirements. Because of wide range of such potential uses, Mayzo, Inc. is not able to recommend this material as safe and effective for such uses and assumes no liability for any such uses. Read and understand the Material Safety Data Sheet before using or handling this product.

FDA Regulations: RA-110W Release Coat does not have any approval for indirect food contact.

The information contained herein is believed to be reliable. However, Mayzo, Inc. makes no warranty, whether expressed or implied, including warranties of merchantability or of fitness for a particular purpose, for the product or products referred to herein. No statements or recommendations contained herein are to be constructed as inducements to infringe any relevant patent, now or hereafter existence. Under no circumstances shall Mayzo, Inc. be liable for incidental, consequential, or other damages from alleged negligence, breach of warranty, strict liability, or any other legal theory, arising out of the use of handling of the product or products referred to herein. The sole remedy of the buyer and sole liability of Mayzo, Inc. for any claims shall be limited to the buyers purchase price of the product which is subject of the claim or the amount actually paid for each product, whichever is less. Technical advice furnished by seller shall not constitute a warranty, which is expressly disclaimed, all such advice being given and accepted at the buyers risk.