



RA-130W Release Coat

Introduction:	RA-130W Release Coat is a non-silicone, acrylic water based emulsion which provides superior release characteristics when applied to polyethylene and polyester films. RA-130W has a strong wetting and adhesion performance with PET and corona treated PE substrates. RA-130W is useful for duct tape and other tapes where an aqueous coating is needed.	
Material Description:	Acrylic emulsion Release Coat	
Chemical Name:	Acrylate	
Empirical Formula:	Proprietary Blend	
CAS #:	Mixture	
Molecular Weight:	Proprietary	
Physical Properties:	Appearance:	Off white, milky emulsion
	Ionic Characteristic:	Nonionic
	Solids Content:	51-52%
	Solvent:	47+% Water
	pH:	4.5 +/- 1
	Specific Gravity:	~1.1
	Viscosity:	<100cps
	Flash point:	>94 °C (>200 °F) [Closed cup]
Mixing Instructions:	Depending on the type of substrate and pressure sensitive adhesive, the concentration of solid matter required should be determined by laboratory trial. RA-130W Release Coat diluted to between 2.0% to 5.0% solids will be adequate in most pressure sensitive applications. Stir well before use.	
Applications:	RA-130W Release Coat is diluted in water to achieve application concentrations. Depending on the substrate and adhesive, the solids concentration should be determined by lab test. Recommended levels are between 2.0 - 5.0%. Film substrates should be corona treated to ensure adhesion to the substrate. Coat at 4 - 5 gm/m ² (wet coat weight) using conventional coating methods with Meyer rod, Anilox or Gravure rollers. Coated substrate must be thoroughly dry before rewinding.	

Advantages:

- Offers an easy peel release. The smooth release properties are similar to PVODC release coatings.
- Cost Efficient. Excellent release can be obtained using as little as 2.0% solids concentration, depending on film, adhesive, coating equipment and desired release levels. The 51-52% solids allow less water to be shipped.
- Low temperature curing.
- A glossy coating
- Can be used with aggressive solvent, hot melt or aqueous acrylic adhesives.

Packaging:

RA-130W Release Coat is available in 480 lb. (217.8 kg) plastic drums and in 2200 lb. (998.2 kg) plastic totes.

Storage:

Keep away from fire and sunlight. Protect eyes and skin from direct contact and avoid inhaling. Do not store below 5°C or over 40°C. Keep container tightly closed.

DO NOT ALLOW THIS PRODUCT TO FREEZE. It will no longer be usable.

Toxicity & Safety:

This material is not intended for use in products for which prolonged contact with mucous membranes or abraded skin, or implantation within the human body is specially intended, unless the finished product has been tested in accordance with the Food and Drug Administration and/or other applicable safety testing requirements. Because of wide range of such potential uses, Mayzo, Inc. is not able to recommend this material as safe and effective for such uses and assumes no liability for any such uses. Read and understand the Material Safety Data Sheet before using or handling this product.

FDA Regulations:

RA-130W Modified Release Coat does not have any approval for indirect food contact.

The information contained herein is believed to be reliable. However, Mayzo, Inc. makes no warranty, whether expressed or implied, including warranties of merchantability or of fitness for a particular purpose, for the product or products referred to herein. No statements or recommendations contained herein are to be constructed as inducements to infringe any relevant patent, now or hereafter existence. Under no circumstances shall Mayzo, Inc. be liable for incidental, consequential, or other damages from alleged negligence, breach of warranty, strict liability, or any other legal theory, arising out of the use of handling of the product or products referred to herein. The sole remedy of the buyer and sole liability of Mayzo, Inc. for any claims shall be limited to the buyers purchase price of the product which is subject of the claim or the amount actually paid for each product, whichever is less. Technical advice furnished by seller shall not constitute a warranty, which is expressly disclaimed, all such advice being given and accepted at the buyers risk.