



Mayzo Makes It Possible

BNX[®] DSTDP


Thioether Antioxidant and Heat Stabilizer

Overview

BNX DSTDP is a thioether antioxidant, or “thiosynergist” used for the protection of plastics, adhesives, elastomers, and petroleum products against thermal oxidative degradation. It shows strong synergistic effects when used in combination with phenolic primary antioxidants.

Chemistry

Chemical Name: Propanoic acid, 3,3'-thiobis-, 1,1'-dioctadecyl ester
CAS Number: 693-36-7
Chemical Structure:



Typical Properties

Product Form: Solid
Melting Range: 64 – 67°C
Molecular Weight: 683.2 g/mol

Solubility (percent by weight, 20°C)

Acetone	1	Methanol	1
Chloroform	20	Methylene chloride	13
Ethanol	1.5	Toluene	10
Ethyl acetate	1.7	Water	<0.01
n-Hexane	1.8		

Applications

BNX DSTDP is a highly effective to improve the long-term thermal stability in a wide range of resins, adhesives, plastics, and lubricants. Combinations of BNX DSTDP with phenolic primary antioxidants (e.g. BNX 1010, BNX 1035, BNX 1076, and others) provide outstanding long-term thermal stability in polyolefins (polypropylene, polyethylene, TPO, including filled grades) for demanding applications such as pipe, power cables, and under-the-hood automotive components. These systems are also highly useful in styrenic polymers (e.g. ABS, HIPS), hot melt adhesives, and lubricants.

Advantages

- Provides excellent protection to polyolefins in high temperature end use applications
- Synergistic performance with phenolic primary antioxidants
- Non-discoloring and non-staining
- Low odor, low volatility
- Broad FDA clearances

Guidelines for Use

Recommended concentrations for use in plastics and adhesives range from 0.05 to 1% by weight. Combinations of BNX DSTDP with primary antioxidants (phenolic antioxidants and multifunctional types) provide synergistic performance. BNX DSTDP is also suitable for use in combination with phosphite process stabilizers and light stabilizers (UV absorbers and benzoates). The exact formulation to be used is dependent on the substrate, performance requirements, and other factors, and should be determined by the user based on testing to simulate actual conditions of use. Please contact Mayzo for specific recommendations.

Storage

This product may be stored up to two years in a sealed container. Containers should be kept tightly closed when not in use and stored in a cool, dry place.

Safety

Please consult the Safety Data Sheet (SDS) prior to handling or using this product.

FDA Regulations

BNX DSTDP is cleared for use in adhesives under 21 CFR §175.105, in resinous and polymeric coatings under 21 CFR §175.300, in semi-rigid and rigid acrylic and modified acrylic plastics under 21 CFR §177.1010, and as an antioxidant employed in the manufacture of food-packaging materials under prior sanction (21 CFR §181.24). Please contact your Mayzo representative for complete details, including restrictions of use.

The information contained herein is believed to be reliable. However, Mayzo, Inc. makes no warranty, whether expressed or implied, including warranties of merchantability or of fitness for a particular purpose, for the product or products referred to herein. No statements or recommendations contained herein are to be constructed as inducements to infringe any relevant patent, now or hereafter existence. Under no circumstances shall Mayzo, Inc. be liable for incidental, consequential, or other damages from alleged negligence, breach of warranty, strict liability, or any other legal theory, arising out of the use of handling of the product or products referred to herein. The sole remedy of the buyer and sole liability of Mayzo, Inc. for any claims shall be limited to the buyers purchase price of the product which is subject of the claim or the amount actually paid for each product, whichever is less. Technical advice furnished by seller shall not constitute a warranty, which is expressly disclaimed, all such advice being given and accepted at the buyers risk.