



## MPM® 1110 Beta Nucleant Masterbatch

**Introduction:** MPM 1110 is a pelletized masterbatch containing a high performance proprietary beta nucleant formulation in a polypropylene homopolymer resin. This masterbatch can be added to non-nucleated and some pigmented polypropylene polymers including homopolymers, random copolymers, and impact copolymers, in order to produce high levels of beta phase crystallinity in extruded sheets, films, and pipes, as well as injection molded parts. This masterbatch is particularly suitable for thick extruded applications that are gray or black colored such as geogrids and certain pipe applications.

**Material Description:** Solid

**Chemical Name:** Polypropylene homopolymer carrier resin plus proprietary additives

**Empirical Formula:** N.A.


**CAS #:** 9003-07-0 (polypropylene)

**Physical Properties:**

Melt Flow Rate:	15 g/10 min.
Melting Range:	Dual melting peaks <sup>(1)</sup> : 150 – 155°C for the beta crystal phase 162 – 167°C for the alpha crystal phase
Specific Gravity (20°C):	0.90 g/cm <sup>3</sup>

(1). As measured on a 1% let-down of the masterbatch in polypropylene homopolymer resin on the second heat using Differential Scanning Calorimetry (DSC) (after cooling from the melt at 10°C/min., and re-heating at 10°C/min.)

## Typical DSC Curves for Non-nucleated PP vs a PP resin containing MPM 1110:



### Applications:

MPM 1110 is specifically designed to beta nucleate a non-nucleated polypropylene resin when used at addition levels in the range of 0.20% to 1.0%. The major application areas for this masterbatch include thick walled extruded products such as pipe and pre-cursor sheet used to make oriented PP geogrids, as well as opaque or pigmented injection molded parts. This masterbatch can also be used for extruded sheet that is used to thermoform PP products. Beta nucleated polypropylene is not suitable for applications requiring high clarity.

### Advantages:

- Can be added at the extruder hopper to produce sheet with high levels of beta crystallinity.
- Broadens the processing window for thermoforming PP, and produces thermoformed parts with more uniform material distribution and improved crush strength and rigidity, with lower sidewall density.
- In pressure and drainage pipe applications the MPM 1110 results in improved impact strength, improved long term creep resistance, and excellent chemical resistance.
- Beta nucleation improves the impact strength and ductility of injection molded or extruded polypropylene without leading to a significant decrease in modulus.
- All of the components of the masterbatch are FDA approved for food contact applications.
- The MPM 1110 will impart a slight gray color into the final part.
- The MPM 1110 can also result in more uniform shrinkage and reduced warpage in extruded and injection molded applications.

### Loading

#### Instructions:

The loading data and results are based on laboratory work (and field-testing) under controlled conditions and do not necessarily indicate the result that the buyer or user will attain. For this reason, we strongly recommend testing of your own system under the actual conditions of processing and end-use prior to full scale testing. The generally recommended loading concentration range is between 0.20% and 1.0% depending on the base polypropylene resin, the

processing conditions used, and the presence of any other additives that may have slight nucleating characteristics such as certain pigments. When added to polypropylene resins that already contain certain weak nucleating additives, the higher end of the addition range should be used.

**FDA Status:**

The components of this product fall under one or more of the following categories for use in contact with food:

- Colorants listed in 21 CFR 178.3297 "*Colorants for Polymers*".
- Components that are exempt from regulation under 21 CFR 170.39 "*Threshold of Regulation for Substances Used in Food Contact Articles*".
- Polymers and/or additives listed in the appropriate parts of 21 CFR (174, 175, 176, 177, 178, 181, 184, and 186).
- Substances that, based on legal opinion, supplier certification, and/or extraction results from food-simulating solvents, are not food additives and are acceptable for this application in full compliance with the Federal Food, Drug, and Cosmetic Act and all applicable food additive regulations.
- Substances that are GRAS (Generally Recognized as Safe) for direct addition to food or for use in contact with food.
- Substances that are "Prior Sanctioned" for use in this application.

**Processing:**

In order to maximize the beta crystal content of extruded sheet, the cast roll should be heated to at least 80°C, and should preferably be in the range of 90 – 130°C. In thick sheet or thick walled applications (thickness > 2mm) lower cooling temperatures can be used successfully. It is also important that no other additives which nucleate the alpha crystalline form, such as clarifying agents, be present in the beta nucleated polypropylene material. Mayzo will provide technical assistance to customers in order to help them optimize the processing conditions for their particular application.

**Toxicity & Safety:**

This material is not intended for use in products for which prolonged contact with mucous membranes or abraded skin, or implantation within the human body is specially intended, unless the finished product has been tested in accordance with the Food and Drug Administration and/or other applicable safety testing requirements. Because of wide range of such potential uses, Mayzo, Inc. is not able to recommend this material as safe and effective for such uses and assumes no liability for any such uses. Read and understand the Material Safety Data Sheet before using or handling this product.

The information contained herein is believed to be reliable. However, Mayzo, Inc. makes no warranty, whether expressed or implied, including warranties of merchantability or of fitness for a particular purpose, for the product or products referred to herein. No statements or recommendations contained herein are to be construed as inducements to infringe any relevant patent, now or hereafter existence. Under no circumstances shall Mayzo, Inc. be liable for incidental, consequential, or other damages from alleged negligence, breach of warranty, strict liability, or any other legal theory, arising out of the use of handling of the product or products referred to herein. The sole remedy of the buyer and sole liability of Mayzo, Inc. for any claims shall be limited to the buyers purchase price of the product which is subject of the claim or the amount actually paid for each product, whichever is less. Technical advice furnished by seller shall not constitute a warranty, which is expressly disclaimed, all such advice being given and accepted at the buyers risk.