



Mayzo Makes It Possible

BLS[®] 3035

UV Absorber / Light Stabilizer for Plastics

Overview


BLS 3035 is a solid cyanoacrylate-type UV absorber used as a light stabilizer in plastics. The product is inherently non-discoloring and is also chemically non-interacting with reactive monomers and polymerization catalysts. It protects the polymers from UV radiation helping to preserve the original appearance and physical integrity.

Chemistry

Chemical Name: 2-Propenoic acid, 2-cyano-3,3-diphenyl-, ethyl ester

CAS Number: 5232-99-5

Chemical Structure:



Typical Properties

Product Form: Solid
Melting Point: 93°C
Molecular Weight: 277.3 g/mol

Solubility (percent by weight, 30°C)

Ethyl acetate	35	Toluene	35
Methanol	7	Water	insoluble
Methyl ethyl ketone (MEK)	45		


Applications

BLS 3035 is highly effective to improve the light stability of a wide range of plastics, including styrenic polymers (ABS, ASA, HIPS, TPE's), PVC (rigid and flexible), polyesters, polyamides, polyurethanes, and acrylics. The product is also useful as a light stabilizer in adhesives and coatings applications. Due to its inherently non-discoloring nature, BLS 3035 is ideal for use in transparent or light-colored substrates. It is also non-interacting with reactive monomers (e.g. isocyanates) and metal-based polymerization catalysts. It is also suitable for use in combination with optical brighteners.

Advantages

- Strong UV absorbance, especially in the UV-B region
- Non-discoloring in plastics, adhesives, and coatings
- Chemically non-interacting with reactive monomers and metal-based polymerization catalysts
- Suitable for use with optical brighteners due to its low long wavelength UV absorbance
- Excellent compatibility with plastics, adhesives, and coating substrates

UV Absorbance Spectrum (10 mg/L in chloroform)



Guidelines for Use

Typical recommended loading levels range between about 0.1 and 2% by weight, depending upon the substrate, processing conditions, end use, and other performance requirements. Combinations with other light stabilizers such as HALS and benzoates often show enhanced performance. The exact formulation to be used is dependent on the substrate, performance requirements, and other factors, and should be determined by the user based on testing to simulate actual conditions of use. Please contact Mayzo for specific recommendations.

Storage

This product may be stored up to two years in a sealed container. Containers should be kept tightly closed when not in use and stored in a cool, dry place.

Safety

Please consult the Safety Data Sheet (SDS) prior to handling or using this product.

FDA Regulations

BLS 3035 has not been cleared by the FDA for use in food contact applications.

The information contained herein is believed to be reliable. However, Mayzo, Inc. makes no warranty, whether expressed or implied, including warranties of merchantability or of fitness for a particular purpose, for the product or products referred to herein. No statements or recommendations contained herein are to be construed as inducements to infringe any relevant patent, now or hereafter existence. Under no circumstances shall Mayzo, Inc. be liable for incidental, consequential, or other damages from alleged negligence, breach of warranty, strict liability, or any other legal theory, arising out of the use of handling of the product or products referred to herein. The sole remedy of the buyer and sole liability of Mayzo, Inc. for any claims shall be limited to the buyers purchase price of the product which is subject of the claim or the amount actually paid for each product, whichever is less. Technical advice furnished by seller shall not constitute a warranty, which is expressly disclaimed, all such advice being given and accepted at the buyers risk.